

VERSION WITH MARKINGS TO SHOW CHANGES MADE

IN THE CLAIMS:

The claims have been amended as follows:

12. (Twice Amended) The foamed laminate based on olefin as claimed in claim 4, wherein the ethylenic thermoplastic elastomer (A) comprises a polypropylene resin (a-3) in an amount of 30 parts by weight or less, per 100 parts by weight of total sum of the polyethylene resin (a-1) and the copolymer based on ethylene/ α -olefin (a-2).

19. (Twice Amended) The foamed laminate based on olefin as claimed in claim 4, wherein the ethylenic thermoplastic elastomer (A) is one which has a compression set of [60 %] 60% or less as determined according to JIS K [7120] 6262 (at 70 °C, 22 hours) and a melt flow rate of 0.1 g/10 min. or higher as determined according to JIS K 7120 (at 230 °C, 10 kg load).